

Inno-Seal 290 ml Black

Art.: 01.2432.0000

290 ml

Inno-Seal is a unique MS polymer based and permanently elastic sealant with adhesive properties. The product is suitable for gluing and sealing and provides good adhesion to many common surfaces such as metal, plastic, rubber and glass. It is very quick to form a skin, fast curing, and extremely flexible.



Base:	Silane modified polymers
Density:	± 1600 kg/m ³
Consistency:	Pasty
Solvents:	No solvents
Hardness:	± 40 (Shore A)
Tensile strength:	± 1,60 N/mm ² (according to DIN 53504)
Elongation at break (%):	± 340% (according to DIN 53504)
Modulus:	± 0,90 N/mm ² (at 100% elongation) (according to DIN 53504)
Shear strength:	1,10 N/mm ² (volgens DIN 53283)
Elastic recovery:	± 70%
Temperature resistance:	-40 °C to +100 °C
UV resistance:	Good. Slight change in colour may appear.
Water resistance:	Good
Solvent resistance:	Moderate
Acid resistance:	Moderate
Slump resistance (constancy):	Good
Percentage of solids:	100%
Shrinkage:	± 4%
Application conditions:	+5°C to +35°C
Type of surface:	Metal, plastic, glass and wood
Surface preparation:	The surface must be clean, dry and free of grease. Clean surfaces with Innotec Multisol or Innotec Seal and Bond Remover . Clean plastic surfaces with Innotec Repaplast Cleaner Antistatic . Plastic, porous or extremely difficult surfaces must be pre-treated with Innotec Repaplast Primer New Formula or Innotec Seal Guard .





Application method:	Apply directly from the cartridge using a glue gun (InnoQuip Pro 2000 Gun , Easy Grip Gun or Air Sealant Applicator 300). When gluing, join the parts together within 10 minutes. If necessary smooth with Innotec Seal Fluid .
Skin formation:	± 10 minutes
Tack free:	± 4 hours
Curing time:	± 3 mm in 24 hours
Minimum joint width:	4 mm
Maximum joint width:	15 mm
Maximum admissible deformation:	20%
Paintability:	Suitable for almost all modern paint or coating systems. Can be sprayed wet-on-wet after 10 minutes using just about any coating system, with no delay in drying. If you want to paint with alkyd paints, add 20% 2K hardener. If you want to spray with 2K lacquers after 4 hours, then apply a plastic primer first (Innotec Repaplast Primer New Formula). Due to the huge variety of paint types on the market, it is best to test the paint beforehand.
Cleaning of materials used:	With Innotec Multisol
Cleaning of hands:	With Innotec Safe Hand Clean Plus and water
Shelf life:	12 months in original, unopened packaging
Storage conditions:	Store cool and dry
Type of batchcode:	F
CE Certification:	Innotec Inno-Seal is a product with CE mark in accordance with Regulation (EU) 305/2011! The corresponding Declaration of Performance (DoP no 0124320100) can be downloaded from our website.
EAN Code:	5400563004630

This technical info sheet replaces all previous versions.

All information is supplied without obligation and based on our knowledge and experience with the product under normal conditions. In practice, the information supplied can in no way replace the tests that need to be performed before first use of the product. Only prior testing of the product can prove whether the product is indeed suitable for the intended application (or not). Thus, we cannot accept any responsibility in case our products are not used in compliance with the advices given.

If the product should not meet the quality requirements, we will only reimburse up to a maximum of the purchase price of the product. We accept no responsibility whatsoever and shall under no circumstances be liable for damage or consequential loss arising from the use of the product.

For information concerning safe use and storage, please refer to the safety data sheet of the product concerned.

