

## Innogrease TF 250 400 g

Art.: 03.0602.9999

400 g

Innogrease TF 250 is an extremely high-grade lubricating grease to which PTFE has been added to obtain a very low frictional resistance and high maintenance intervals.



Base:	Lithium complex
Density:	940 kg/m <sup>3</sup>
Consistency:	Pasty (solid)
Viscosity:	2 (according to NLGI)
Flash point:	> 150°C
Pressure resistance:	4 ball welding load: 280 kg (according to IP-239)
Temperature resistance:	-30°C to +150°C
Peak temperature resistance:	225°C
Drop point:	250°C to 300°C
Water resistance:	Very good
Saltwater resistance:	Moderate
Acid resistance:	Resistant to diluted acids
Corrosion resistance:	0-0 (according to Emcor ISO 11 007)
Mechanical stability:	Good
Percentage of greasing agent:	100% (of which 2% PTFE)
Tests:	Penetration at 25°C and 60 strokes to ASTM D-217 = 280
Application conditions:	-10°C to +40°C
Type of surface:	Almost all kinds of surfaces
Surface preparation:	The surface must be clean, dry, free of grease and non-corroded. Clean surfaces with Innotec <a href="#">Multisol</a> , Innotec <a href="#">Ultra Clean</a> or Innotec <a href="#">Power Clean</a> .
Application method:	Depending on the application, apply directly from the cartridge using for example a brush or grease gun (Innotec <a href="#">Lube Shuttle Gun</a> ).
Cleaning of materials used:	With Innotec <a href="#">Multisol</a> or Innotec <a href="#">Power Clean</a>
Cleaning of hands:	With Innotec <a href="#">Safe Hand Clean Plus</a> and water





Shelf life: 10 years in original, unopened packaging

---

Storage conditions: Store cool and dry

---

Type of batchcode: F

---

EAN Code: 5400563016121

This technical info sheet replaces all previous versions.

All information is supplied without obligation and based on our knowledge and experience with the product under normal conditions. In practice, the information supplied can in no way replace the tests that need to be performed before first use of the product. Only prior testing of the product can prove whether the product is indeed suitable for the intended application (or not). Thus, we cannot accept any responsibility in case our products are not used in compliance with the advices given.

If the product should not meet the quality requirements, we will only reimburse up to a maximum of the purchase price of the product. We accept no responsibility whatsoever and shall under no circumstances be liable for damage or consequential loss arising from the use of the product.

For information concerning safe use and storage, please refer to the safety data sheet of the product concerned.

